

ONIRO
PO Box 180
3700 A.D. Zeist
Nederland



Your notice of
28-08-2013

Your reference

Date
16-09-2013

Analysis Report 13.03933.02

Required tests :

NF P 92-503 (1995)

**Classification of materials according to their reaction to fire -
"Electric burner"**

Identification number	Information given by the client	Date of receipt
T1312833	Niroxx	28-08-2013

Pros Van Hoeyland

Order responsible

This report runs to 2 pages and may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.

The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples. In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

VAT BE 0459.218.289

Fin. Acc. 210-0472965-45

IBAN BE44 2100 4729 6545

CENTEXBEL-GENT
Technologiepark 7
BE-9052 Zwijnaarde
Tel. + 32 9 220 41 51 • Fax + 32 9 220 49 55
gent@centexbel.be

CENTEXBEL-VERVIERS
Avenue du Parc 38
BE-4650 Herve (Chaineux)
Tel. + 32 87 32 24 30 Fax + 32 87 34 05 18
chaineux@centexbel.be

Reference: T1312833 - Niroxx

Classification of materials according to their reaction to fire - "Electric burner"

Date of ending the test 12-09-2013
 Standard used NF P 92-503 (1995)
 Product standard NF P 92-507 (2004)

Deviation from the standard -

Sample thickness ≤ 5 mm

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure

Conditioning 23°C, relative humidity 50%
 Minimum 7 days or until constant mass is achieved

Only the front side has been tested

	Length		Width	
	1	2	1	2
Hole formation	no	no	no	no
Max. afterflame time (s)	10	12	8	24
Afterglow	yes	yes	yes	yes
Afterglow with propagation in area > 25 cm	no	no	no	no
Damaged length (cm)	19.0	20.0	19.5	21.5
Damaged width (cm) in area >45 cm	0	0	0	0
Flaming molten droplets	no	no	no	no
Non-flaming molten droplets	no	no	no	no
Flaming debris	no	no	no	no
Non-flaming debris	no	no	no	no
Average damaged length (cm)	20.0			
Average damaged width (cm) in area > 45 cm	0			

Classification M2