

Our Ref: SW/MG/BR

1 February 2013

Report 197423

Page 1 of 2

Oniro B.V. Postbus 180 3700 AD Zeist

DATE RECEIVED

QUALITY REFERENCE REPUTED FIBRE CONTENT

COLOUR DESIGN FABRIC DESCRIPTION : 30 JANUARY 2013

: FABRIXX FLATLINE/HEARTBEAT

: NOT GIVEN

: MULTI : WOVEN

**REQUEST:** 

Abrasion

COMMENTS: Flammability to follow on report 197423/2

S. WISEMAN LABORATORY MANAGER

M. GRAINGER SENIOR TECHNOLOGIST

This report may not be reproduced except in full without the written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Opinions and interpretations expressed herein are outside the scope of





Report 197423

**PHYSICAL** 

06 February 2013

Page 2 of 2

BS EN ISO 12947:1998 ABRASION - END POINT 12 kPa Load

Number of rubs to breakdown:

> 35,000