

Oniro BV
Woudenbergseweg 19C10
2707 HW ZEIST
Nederland



Your notice of
09-11-2016

Your reference
4500273597-96

Date
25-11-2016

Analysis Report 16.05981.04

Required tests :

ISO 105-B02 (2014)

Determination of the colour fastness to light

Identification number	Information given by the client	Date of receipt
T1621939	PUxx Nr.2	09-11-2016

Bea De Paepe

Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

CENTEXBEL • textile competence centre • www.centexbel.be • www.vkc.be
Inrichting erkend bij toepassing van de besluitwet van 30-01-1947 • Établissement reconnu par application de l'arrêté-loi du 30-01-1947
GENT • Technologiepark 7 • BE-9052 Zwijnaarde, Belgium • phone +32 9 220 41 51 • fax +32 9 220 49 55 • gent@centexbel.be
GRÂCE-HOLLOGNE • Rue du Travail 5 • BE-4460 Grâce-Hollogne, Belgium • phone +32 4 296 82 00 • g-h@centexbel.be
KORTRIJK • Etienne Sabbelaan 49 • BE-8500 Kortrijk, Belgium • phone +32 56 281828 • fax +32 56 281830 • info@vkc.be
VAT BE 0459.218.289 • IBAN BE44 2100 4729 6545 • BIC GEBABEBB

Reference: T1621939 - PUxx Nr.2

Determination of the colour fastness to light

Date of ending the test	24-11-2016
Standard used	ISO 105-B02 (2014)
Deviation from the standard	-
Method	1
Apparatus	Xenotest 220+ Atlas
Exposure	Constant
Irradiance	42 W/m ² @ 300-400 nm
Black standard temperature	47±3°C
Effective humidity	±40%

Assessment according the blue scale standard

Numerical rating Blue scale grade 7

Annex 1 Exposed sample in annex